

Belice Group

SENSAMİN C

(Katyonik Spesial Yumuşatıcı)

KİMYASAL YAPISI : Yüksek yağ asitleri amin bileşikleri antistatik ve hidrokarbonların

Sinergetik kombinasyonu

Görünümü : Krem rengi emülsiyon
İyonik Yapısı : Katyonik
Çözünürlüğü : Her oranda su ile kolayca çözülür.

KULLANIM ALANI : SENSAMİN C Pamuk , Viskon Polyester , akrilik elyaftan ve bunların Birbirleriyle olan karışımlarından yapılmış ipliklerin bobin boyama ve çile boyama sonrasında ipliğe kaygan , parlak , dolgun , yumuşak , antistatik bir özellik verir. İpliklerin aktarmada kolayca aktarılmasını sağlar. Tüylenemeyi ve kopuşları önler. Örgülü mallarda yumuşak , kaygan ve dolgun bir tutum kazandırır. Konfeksiyonda dikiş kolaylığı sağlar.

UYGULAMA ŞEKLİ :

Çekirme sistemlerinde :

Banyo oranı : 1:10
3 % SENSAMİN C
ph : 5 – 5,5
40-45 ° C' de 20 dakika
bobin boyamada banyo sirkülasyonu her iki yönde çalışmalı!..

- Fularlama sistemlerinde :

20 – 30 gr/lit SENSAMİN C
Soğukta : 25-30 ° C' de
Sıkma : % 70
Kurutma : 130 ° C

DEPOLANMASI : Normal depolama şartlarında 1 yıldır. Soğuktan donmaya karşı ve aşırı ısıya karşı korunmalıdır

SENSAMIN C

(Cationic specialty softener)

CHEMICAL COMPOSITION : A synergetic combination of high fatty acids amine compounds, antistatic substances, and hydrocarbons

Appearance : Cream colored emulsion
Ionic nature : Cationic
Solubility : Easily soluble with water in all proportions

PROPERTIES : SENSAMIN C imparts slippery, bright, full, soft touch and antistatic properties to the yarn produced from cotton, viscone, polyester, acrylic fibers and their blends after package and hank dyeing. Provides running easily in yarn transferring operations. Prevents yarn hairiness and breakages. Confers a soft, slippery and full touch to knitted fabrics. Improves sewability in ready-made clothing operations.

APLICATION :

In exhaust treatments:

Liquor Ratio : 1:10
3% SENSAMIN C
pH 5 – 5.5
for 20 min at 40 - 45°C
Must be worked with double directional circulation in package dyeing!

In padding treatments:

20 – 30 g/l SENSAMIN C
Padding : 25 - 30°C
Pick up : 70 %
Drying : 130 °C

STORAGE : 1 year under normal storage condition. Must be protected from freezing and excess heat